

| Hole | From (m) | To (m) | Thickness (m) | % Ni | % Co |
|-------------|----------|--------|---------------|-------|-------|
| MAM-KK-0054 | 13.02 | 14.05 | 1.03 | 0.78 | 0.058 |
| | 14.05 | 15.3 | 1.25 | 0.788 | 0.056 |
| | 15.3 | 16.3 | 1 | 0.943 | 0.157 |
| | 16.3 | 16.82 | 0.52 | 0.989 | 0.181 |
| | 16.9 | 18 | 1.1 | 1.18 | 0.153 |
| | 18 | 18.95 | 0.95 | 1.26 | 0.064 |
| | 18.95 | 20.1 | 1.15 | 0.394 | 0.013 |
| | 20.1 | 21.14 | 1.04 | 0.274 | 0.012 |

| Hole | From (m) | To (m) | Thickness (m) | % Ni | % Co |
|-------------|-----------------|---------------|----------------------|-------------|-------------|
| MAM-KK-0044 | 3.55 | 4.6 | 1.05 | 0.248 | 0.024 |
| | 4.6 | 5.5 | 0.9 | 0.407 | 0.089 |
| | 5.5 | 6.5 | 1 | 0.229 | 0.012 |
| | 6.5 | 7.5 | 1 | 0.301 | 0.012 |

| Hole | From (m) | To (m) | Thickness (m) | % Ni | % Co |
|-------------|----------|--------|---------------|-------|-------|
| MAM-KK-0026 | 0.4 | 1.3 | 0.9 | 0.581 | 0.052 |
| | 1.3 | 2.6 | 1.3 | 0.834 | 0.076 |
| | 2.6 | 3.9 | 1.3 | 1.06 | 0.082 |
| | 3.9 | 5 | 1.1 | 1.1 | 0.043 |
| | 5 | 6.3 | 1.3 | 0.791 | 0.076 |
| | 6.3 | 7.3 | 1 | 0.963 | 0.069 |
| | 7.3 | 8.3 | 1 | 1.38 | 0.09 |
| | 8.3 | 9.2 | 0.9 | 1.03 | 0.069 |
| | 9.3 | 10.3 | 1 | 0.973 | 0.106 |
| | 10.3 | 11.55 | 1.25 | 0.948 | 0.082 |
| | 11.55 | 12 | 0.45 | 0.62 | 0.043 |
| | 12 | 13.15 | 1.15 | 0.94 | 0.112 |
| | 13.15 | 13.6 | 0.45 | 0.272 | 0.115 |
| | 13.6 | 14.5 | 0.9 | 0.983 | 0.098 |
| | 14.5 | 15.35 | 0.85 | 0.672 | 0.065 |
| | 15.35 | 16.4 | 1.05 | 1.02 | 0.074 |
| | 16.4 | 17.4 | 1 | 0.712 | 0.056 |
| | 17.4 | 18.4 | 1 | 1.02 | 0.102 |
| | 18.4 | 19 | 0.6 | 1.18 | 0.202 |
| | 19 | 20.2 | 1.2 | 1.07 | 0.22 |
| | 20.2 | 21 | 0.8 | 0.828 | 0.098 |
| | 21 | 21.7 | 0.7 | 1.36 | 0.139 |
| | 21.7 | 22.85 | 1.15 | 1.24 | 0.09 |
| | 22.85 | 24.1 | 1.25 | 1.42 | 0.105 |
| | 24.1 | 24.85 | 0.75 | 1.2 | 0.075 |
| | 24.85 | 25.8 | 0.95 | 1.12 | 0.115 |
| | 25.98 | 27 | 1.02 | 0.58 | 0.053 |
| | 27 | 28.25 | 1.25 | 0.863 | 0.065 |
| | 28.25 | 29.53 | 1.28 | 1.26 | 0.091 |
| | 29.7 | 30.95 | 1.25 | 0.704 | 0.072 |
| | 30.95 | 32.15 | 1.2 | 0.952 | 0.111 |
| | 32.15 | 33.15 | 1 | 1.19 | 0.124 |
| | 33.15 | 34.15 | 1 | 1.21 | 0.057 |
| | 34.15 | 35.15 | 1 | 1.21 | 0.018 |
| | 35.15 | 36.05 | 0.9 | 0.751 | 0.014 |
| | 36.05 | 36.9 | 0.85 | 0.718 | 0.015 |
| | 36.9 | 37.4 | 0.5 | 0.567 | 0.012 |
| 37.4 | 37.88 | 0.48 | 0.352 | 0.011 | |

| Hole | From (m) | To (m) | Thickness (m) | % Ni | % Co |
|-------------|----------|--------|---------------|-------|-------|
| MAM-KK-0037 | STD | | | | |
| | 5 | 5.55 | 0.55 | 0.112 | 0.012 |
| | 5.55 | 6.25 | 0.7 | 0.38 | 0.047 |
| | 6.25 | 7 | 0.75 | 0.415 | 0.088 |
| | 7 | 8.2 | 1.2 | 0.221 | 0.033 |
| | 8.2 | 9.2 | 1 | 0.804 | 0.083 |
| | 9.2 | 10.2 | 1 | 0.897 | 0.085 |
| | 10.2 | 11.2 | 1 | 1.07 | 0.093 |
| | 11.2 | 12.1 | 0.9 | 1.13 | 0.089 |
| | 12.1 | 13.3 | 1.2 | 0.27 | 0.013 |
| | 13.3 | 13.9 | 0.6 | 0.686 | 0.051 |
| | 13.9 | 14.9 | 1 | 0.328 | 0.019 |
| | 14.9 | 15.8 | 0.9 | 0.828 | 0.072 |
| | 15.8 | 16.65 | 0.85 | 0.811 | 0.059 |
| | 16.65 | 17.95 | 1.3 | 1.07 | 0.069 |
| | 17.95 | 18.55 | 0.6 | 0.593 | 0.032 |
| | 18.55 | 19.35 | 0.8 | 1.1 | 0.055 |
| | 19.35 | 20.35 | 1 | 1.12 | 0.042 |
| | 20.35 | 21.35 | 1 | 0.597 | 0.023 |
| | 21.35 | 21.8 | 0.45 | 0.523 | 0.012 |
| | 21.8 | 22.6 | 0.8 | 1.1 | 0.021 |
| | 22.6 | 23.2 | 0.6 | 0.622 | 0.01 |
| | 23.2 | 24.5 | 1.3 | 0.595 | 0.014 |
| | 24.5 | 25.8 | 1.3 | 0.671 | 0.016 |
| | 25.8 | 27.1 | 1.3 | 0.957 | 0.017 |
| | 27.1 | 27.8 | 0.7 | 1.14 | 0.013 |
| | 27.8 | 28.6 | 0.8 | 0.65 | 0.01 |
| | 28.8 | 29.6 | 0.8 | 0.443 | 0.008 |
| | 29.6 | 30.55 | 0.95 | 0.627 | 0.01 |
| | 30.55 | 30.8 | 0.25 | 1.11 | 0.01 |
| | 30.8 | 31.5 | 0.7 | 0.87 | 0.016 |
| | 31.5 | 32.3 | 0.8 | 0.826 | 0.012 |
| | 32.3 | 32.85 | 0.55 | 0.641 | 0.012 |
| | 32.85 | 33.2 | 0.35 | 0.633 | 0.011 |
| | 33.2 | 34.1 | 0.9 | 0.273 | 0.009 |
| | 34.1 | 34.64 | 0.54 | 0.325 | 0.008 |

| Hole | From (m) | To (m) | Thickness (m) | % Ni | % Co |
|-------------|----------|--------|---------------|-------|-------|
| MAM-KK-0055 | 4.55 | 4.95 | 0.4 | 0.085 | 0.001 |
| | 4.95 | 5.65 | 0.7 | 0.401 | 0.02 |
| | 5.65 | 6.6 | 0.95 | 0.686 | 0.041 |
| | 6.6 | 7.4 | 0.8 | 0.801 | 0.083 |
| | 7.4 | 8.4 | 1 | 0.795 | 0.056 |
| | 8.4 | 9.5 | 1.1 | 0.87 | 0.091 |
| | 9.5 | 10.6 | 1.1 | 0.743 | 0.079 |
| | 10.6 | 11.85 | 1.25 | 0.646 | 0.109 |
| | 11.85 | 12.8 | 0.95 | 0.649 | 0.063 |
| | 12.8 | 13.1 | 0.3 | 0.722 | 0.076 |
| | 13.1 | 14 | 0.9 | 0.915 | 0.046 |
| | 14 | 15 | 1 | 0.792 | 0.194 |
| | 15 | 16 | 1 | 0.722 | 0.33 |
| | 16 | 17 | 1 | 0.619 | 0.133 |
| | 17 | 18 | 1 | 0.679 | 0.126 |
| | 18 | 18.9 | 0.9 | 1.37 | 0.272 |
| | 18.9 | 20 | 1.1 | 1.21 | 0.129 |
| | 20 | 21 | 1 | 0.734 | 0.148 |
| | 21 | 22 | 1 | 0.911 | 0.398 |
| | 22 | 22.95 | 0.95 | 0.756 | 0.284 |
| | 22.95 | 24 | 1.05 | 0.967 | 0.149 |
| | 24 | 25 | 1 | 1.31 | 0.287 |
| | 25 | 26 | 1 | 1.28 | 0.25 |
| 26 | 27 | 1 | 0.749 | 0.151 | |
| 27.15 | 27.6 | 0.45 | 0.126 | 0.014 | |
| 27.84 | 29 | 1.16 | 0.282 | 0.012 | |
| STD | | | | | |

| Hole | From (m) | To (m) | Thickness (m) | % Ni | % Co |
|-------------|----------|--------|---------------|-------|-------|
| MAM-KK-0056 | 5.4 | 5.95 | 0.55 | 0.045 | 0.003 |
| | 5.95 | 7.2 | 1.25 | 0.267 | 0.013 |
| | 7.2 | 8.2 | 1 | 0.355 | 0.016 |
| | 8.2 | 9.35 | 1.15 | 0.33 | 0.009 |
| | 9.35 | 10.35 | 1 | 0.528 | 0.051 |
| | 10.35 | 11 | 0.65 | 0.536 | 0.1 |
| | 11 | 12 | 1 | 0.544 | 0.062 |
| | 12 | 13.05 | 1.05 | 0.861 | 0.074 |
| | 13.05 | 14 | 0.95 | 0.878 | 0.117 |
| | 14 | 14.8 | 0.8 | 0.844 | 0.183 |
| | 14.8 | 15.7 | 0.9 | 0.859 | 0.115 |
| | 15.7 | 16.6 | 0.9 | 0.751 | 0.131 |
| | 16.6 | 17.2 | 0.6 | 0.956 | 0.137 |
| | 17.2 | 18.05 | 0.85 | 1.64 | 0.073 |
| | 18.05 | 18.4 | 0.35 | 0.495 | 0.011 |
| | 18.4 | 19 | 0.6 | 0.37 | 0.025 |
| | 19 | 19.6 | 0.6 | 0.296 | 0.012 |
| | 19.7 | 20.5 | 0.8 | 1.31 | 0.029 |
| | 20.5 | 21.5 | 1 | 0.809 | 0.012 |
| | 21.5 | 21.8 | 0.3 | 1.64 | 0.029 |
| | 21.8 | 22.95 | 1.15 | 0.516 | 0.013 |
| | 22.95 | 24.2 | 1.25 | 1.16 | 0.022 |
| | 24.2 | 25.2 | 1 | 0.472 | 0.012 |
| | 25.2 | 26.3 | 1.1 | 1.07 | 0.033 |
| | 26.3 | 27.3 | 1 | 1.58 | 0.024 |
| | 27.3 | 28.5 | 1.2 | 0.345 | 0.011 |

| Hole | From (m) | To (m) | Thickness (m) | % Ni | % Co |
|-------------|-----------------|---------------|----------------------|-------------|-------------|
| MAM-KK-0045 | 2.85 | 3.25 | | 0.036 | 0.003 |
| | 3.25 | 4.15 | | 0.253 | 0.055 |
| | 4.15 | 5 | | 0.198 | 0.01 |

| Hole | From (m) | To (m) | Thickness (m) | % Ni | % Co | |
|-------------|----------|--------|---------------|-------|-------|--|
| MAM-KK-0046 | 3.85 | 4.2 | 0.35 | 0.245 | 0.019 | |
| | 4.25 | 5 | 0.75 | 0.528 | 0.042 | |
| | 5 | 5.75 | 0.75 | 0.357 | 0.047 | |
| | 5.8 | 6.95 | 1.15 | 0.388 | 0.054 | |
| | 6.95 | 7.75 | 0.8 | 0.557 | 0.062 | |
| | 7.75 | 8.55 | 0.8 | 0.743 | 0.154 | |
| | 8.55 | 9.3 | 0.75 | 0.448 | 0.049 | |
| | 9.3 | 10.3 | 1 | 0.304 | 0.011 | |
| | 10.3 | 11.2 | 0.9 | 0.428 | 0.011 | |
| | 11.4 | 12.6 | 1.2 | 1.01 | 0.057 | |
| | 12.6 | 13.4 | 0.8 | 1.2 | 0.023 | |
| | 13.4 | 14.65 | 1.25 | 0.528 | 0.012 | |
| | 14.7 | 15.95 | 1.25 | 0.259 | 0.01 | |
| | 15.95 | 17 | 1.05 | 0.269 | 0.011 | |
| | 17 | 17.8 | 0.8 | 1.34 | 0.034 | |
| | STD | | | | | |
| | 17.8 | 18.3 | 0.5 | 0.499 | 0.011 | |
| | 18.3 | 18.6 | 0.3 | 0.912 | 0.016 | |
| | 18.6 | 18.95 | 0.35 | 0.51 | 0.011 | |
| | 18.95 | 20.15 | 1.2 | 0.558 | 0.012 | |
| | 20.15 | 21.2 | 1.05 | 0.78 | 0.013 | |
| | 21.2 | 22.5 | 1.3 | 0.622 | 0.014 | |
| | 22.5 | 23.3 | 0.8 | 0.426 | 0.012 | |

| Hole | From (m) | To (m) | Thickness (m) | % Ni | % Co |
|-------------|----------|--------|---------------|-------|-------|
| MAM-KK-0040 | 4.05 | 5 | 0.95 | 0.707 | 0.016 |
| | 5 | 5.85 | 0.85 | 0.812 | 0.015 |
| | 5.9 | 7.2 | 1.3 | 0.863 | 0.016 |
| | 7.2 | 8.35 | 1.15 | 0.936 | 0.028 |
| | 8.35 | 9.5 | 1.15 | 1.16 | 0.015 |
| | 9.6 | 10.5 | 0.9 | 1.01 | 0.02 |
| | 10.5 | 11.4 | 0.9 | 1.28 | 0.051 |
| | 11.4 | 12.3 | 0.9 | 0.972 | 0.03 |
| | 12.3 | 13.31 | 1.01 | 0.99 | 0.086 |
| | 13.5 | 14.8 | 1.3 | 1.22 | 0.083 |
| | 14.8 | 15.1 | 0.3 | 1.27 | 0.218 |
| | 15.1 | 15.6 | 0.5 | 1.05 | 0.178 |
| | 15.6 | 16.62 | 1.02 | 1.46 | 0.039 |
| | 16.7 | 17 | 0.3 | 0.516 | 0.014 |
| | 17 | 18 | 1 | 2.32 | 0.049 |
| | 18 | 18.85 | 0.85 | 0.345 | 0.011 |
| | 18.85 | 20.1 | 1.25 | 1.59 | 0.035 |
| | 20.1 | 20.35 | 0.25 | 0.393 | 0.012 |
| | 20.35 | 21.6 | 1.25 | 1.39 | 0.027 |
| | 21.6 | 22.15 | 0.55 | 2.18 | 0.021 |
| | 22.15 | 22.66 | 0.51 | 0.783 | 0.011 |
| | 22.66 | 23.65 | 0.99 | 0.909 | 0.018 |
| | 23.65 | 24.8 | 1.15 | 0.635 | 0.012 |
| | 24.8 | 25.35 | 0.55 | 0.28 | 0.011 |
| | 25.35 | 26.4 | 1.05 | 1.27 | 0.043 |
| | 26.4 | 27.4 | 1 | 1.18 | 0.071 |
| | 27.4 | 28.24 | 0.84 | 0.622 | 0.025 |
| | 28.9 | 29.85 | 0.95 | 0.44 | 0.023 |
| | 29.85 | 30.3 | 0.45 | 0.318 | 0.016 |

| Hole | From (m) | To (m) | Thickness (m) | % Ni | % Co |
|-------------|-----------------|---------------|----------------------|-------------|-------------|
| MAM-KK-0038 | 4.22 | 4.78 | 0.56 | 0.013 | 0.003 |
| | 4.95 | 6.1 | 1.15 | 0.138 | 0.02 |
| | 6.1 | 7 | 0.9 | 0.37 | 0.133 |
| | 7 | 7.5 | 0.5 | 0.216 | 0.01 |
| | 7.5 | 8.6 | 1.1 | 0.302 | 0.016 |
| | 8.6 | 9.5 | 0.9 | 0.202 | 0.01 |

| Hole | From (m) | To (m) | Thickness (m) | % Ni | % Co |
|-------------|----------|--------|---------------|-------|-------|
| MAM-KK-0039 | 5 | 6 | 1 | 0.14 | 0.008 |
| | 6 | 7 | 1 | 0.141 | 0.011 |
| | 7 | 7.9 | 0.9 | 0.216 | 0.016 |
| | 7.9 | 8.55 | 0.65 | 0.43 | 0.065 |
| | 8.55 | 9.15 | 0.6 | 0.399 | 0.063 |
| | 9.2 | 9.5 | 0.3 | 0.199 | 0.011 |
| | 9.5 | 10.2 | 0.7 | 0.354 | 0.051 |
| | 10.2 | 10.9 | 0.7 | 0.259 | 0.037 |
| | 10.9 | 12 | 1.1 | 0.341 | 0.057 |
| | 12 | 13 | 1 | 0.8 | 0.06 |
| | 13 | 13.75 | 0.75 | 0.46 | 0.036 |
| | 13.75 | 14.75 | 1 | 0.583 | 0.042 |
| | 14.75 | 15.3 | 0.55 | 0.825 | 0.064 |
| | 15.3 | 15.7 | 0.4 | 0.551 | 0.018 |
| | 15.7 | 16.6 | 0.9 | 0.583 | 0.022 |
| | 16.6 | 17.2 | 0.6 | 0.532 | 0.021 |
| | 17.2 | 17.9 | 0.7 | 0.287 | 0.017 |
| | 17.9 | 19.1 | 1.2 | 0.275 | 0.012 |
| | 19.1 | 20.3 | 1.2 | 0.272 | 0.011 |
| | 20.3 | 21.5 | 1.2 | 0.297 | 0.011 |
| | 21.5 | 21.9 | 0.4 | 0.485 | 0.038 |
| | 21.9 | 22.9 | 1 | 1.29 | 0.06 |
| | 22.9 | 23.7 | 0.8 | 1.56 | 0.051 |
| | 23.7 | 24.8 | 1.1 | 0.635 | 0.014 |
| | 24.8 | 25.9 | 1.1 | 0.484 | 0.018 |
| | 25.9 | 27 | 1.1 | 0.437 | 0.016 |
| 27 | 28 | 1 | 0.314 | 0.011 | |

| Hole | From (m) | To (m) | Thickness (m) | % Ni | % Co |
|-------------|----------|--------|---------------|-------|-------|
| MAM-KK-0071 | 4 | 5.25 | 1.25 | 0.643 | 0.029 |
| | 5.25 | 6.5 | 1.25 | 0.656 | 0.045 |
| | 6.5 | 7.75 | 1.25 | 1.04 | 0.08 |
| | 7.75 | 9 | 1.25 | 0.73 | 0.166 |
| | 9 | 10.35 | 1.35 | 0.33 | 0.105 |
| | 10.6 | 11.8 | 1.2 | 0.744 | 0.051 |
| | 11.8 | 13 | 1.2 | 1.11 | 0.025 |
| | 13 | 14.2 | 1.2 | 1.04 | 0.045 |
| | 14.2 | 15.1 | 0.9 | 0.864 | 0.044 |
| | 15.1 | 16 | 0.9 | 0.606 | 0.127 |
| | 16.3 | 17 | 0.7 | 0.518 | 0.125 |
| | 17 | 17.66 | 0.66 | 0.254 | 0.063 |
| | 17.9 | 18.6 | 0.7 | 0.628 | 0.083 |
| | 18.6 | 19.3 | 0.7 | 0.712 | 0.068 |
| | 19.3 | 20 | 0.7 | 0.414 | 0.015 |
| | 20 | 20.7 | 0.7 | 0.495 | 0.014 |
| | 20.7 | 21.4 | 0.7 | 0.388 | 0.015 |
| | 21.4 | 22.6 | 1.2 | 0.476 | 0.034 |
| | 23.1 | 23.7 | 0.6 | 0.411 | 0.04 |
| | 24 | 24.7 | 0.7 | 0.429 | 0.05 |
| 24.7 | 25.4 | 0.7 | 0.376 | 0.053 | |
| 25.4 | 26.2 | 0.8 | 0.99 | 0.066 | |
| 26.2 | 27 | 0.8 | 0.887 | 0.037 | |
| 27 | 28 | 1 | 0.462 | 0.05 | |
| 28 | 29 | 1 | 0.387 | 0.046 | |
| 29 | 30.2 | 1.2 | 0.46 | 0.061 | |

| Hole | From (m) | To (m) | Thickness (m) | % Ni | % Co |
|--------------|----------|--------|---------------|-------|-------|
| MAM-KK-0047A | 4 | 5.2 | 1.2 | 0.018 | 0.001 |
| | 5.2 | 6.4 | 1.2 | 0.241 | 0.008 |
| | 6.4 | 7.6 | 1.2 | 0.601 | 0.035 |
| | 7.6 | 8.8 | 1.2 | 0.675 | 0.067 |
| | 8.8 | 10 | 1.2 | 0.791 | 0.106 |
| | 10 | 11.2 | 1.2 | 0.858 | 0.062 |
| | 11.2 | 12.4 | 1.2 | 1.08 | 0.099 |
| | 12.4 | 13.6 | 1.2 | 0.724 | 0.081 |
| | 13.6 | 14.8 | 1.2 | 0.758 | 0.052 |
| | 14.8 | 16 | 1.2 | 0.932 | 0.065 |
| | 16 | 16.85 | 0.85 | 0.714 | 0.016 |
| | 16.85 | 17.85 | 1 | 2.13 | 0.049 |
| | 17.85 | 18.2 | 0.35 | 0.976 | 0.014 |
| | 18.2 | 19.1 | 0.9 | 1.65 | 0.038 |
| | 19.1 | 19.8 | 0.7 | 0.845 | 0.015 |
| | 19.8 | 20.8 | 1 | 0.971 | 0.022 |
| | 20.8 | 21.6 | 0.8 | 0.451 | 0.012 |
| | 21.6 | 22.7 | 1.1 | 0.994 | 0.03 |
| | 22.7 | 23.75 | 1.05 | 0.604 | 0.015 |
| | 23.75 | 24.75 | 1 | 0.829 | 0.026 |
| | 24.75 | 25.25 | 0.5 | 0.439 | 0.013 |
| | 25.25 | 26.5 | 1.25 | 0.576 | 0.02 |
| | 26.5 | 27.75 | 1.25 | 0.456 | 0.013 |
| | 27.75 | 29 | 1.25 | 0.248 | 0.01 |
| | 29 | 30 | 1 | 0.495 | 0.043 |
| | 30 | 30.95 | 0.95 | 0.484 | 0.021 |
| | 30.95 | 31.85 | 0.9 | 0.381 | 0.02 |
| | 31.85 | 32.1 | 0.25 | 0.247 | 0.01 |

| Hole | From (m) | To (m) | Thickness (m) | % Ni | % Co |
|-------------|----------|--------|---------------|-------|--------|
| MAM-KK-0049 | 4 | 5.25 | 1.25 | 0.02 | 0.002 |
| | 5.25 | 6.5 | 1.25 | 0.028 | <0.001 |
| | 6.5 | 7.75 | 1.25 | 0.301 | 0.011 |
| | 7.75 | 9 | 1.25 | 0.208 | 0.008 |
| | 9 | 10.25 | 1.25 | 0.301 | 0.02 |
| | 10.25 | 11.5 | 1.25 | 0.36 | 0.028 |
| | 11.5 | 12.75 | 1.25 | 0.377 | 0.037 |
| | 12.75 | 14 | 1.25 | 0.313 | 0.054 |
| | 14 | 15 | 1 | 0.348 | 0.056 |
| | 15 | 15.9 | 0.9 | 0.876 | 0.09 |
| | 15.9 | 16.75 | 0.85 | 1.29 | 0.075 |
| | 16.85 | 17.35 | 0.5 | 1.99 | 0.04 |
| | 17.35 | 18.45 | 1.1 | 1.5 | 0.037 |

| Hole | From (m) | To (m) | Thickness (m) | % Ni | % Co |
|-------------|----------|--------|---------------|-------|-------|
| MAM-KK-0057 | 0.55 | 0.7 | | | |
| | 5.05 | 5.3 | | | |
| | 8.15 | 8.4 | | | |
| | 11.35 | 12.15 | 0.8 | 0.097 | 0.003 |
| | 12.15 | 12.4 | | | |
| | 12.4 | 13.5 | 1.1 | 0.193 | 0.012 |
| | 13.5 | 14.1 | 0.6 | 0.136 | 0.014 |
| | 14.1 | 14.65 | 0.55 | 0.264 | 0.009 |