

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0093	3.1	4	0.9	0.006	0.001
	4	5.13	1.13	<0.005	0.001
	5.4	6.03	0.63	0.024	<0.001
	6.03	6.9	0.87	0.169	0.018
	6.9	7.7	0.8	0.383	0.058
	7.7	8.7	1	0.841	0.141
	8.7	9.6	0.9	0.407	0.064
	9.6	10.4	0.8	0.276	0.06
	10.4	11	0.6	0.763	0.099
	11	11.87	0.87	0.551	0.047
	11.87	12.06	0.19	0.328	0.025
	12.1	13.3	1.2	0.509	0.046
	13.3	13.95	0.65	0.466	0.029
	13.95	14.47	0.52	0.708	0.03
	14.47	15.5	1.03	0.223	0.01
	15.5	16.6	1.1	0.228	0.02
	16.6	17.1	0.5	0.193	0.012
	17.1	18.1	1	0.515	0.038
	18.1	19.1	1	0.351	0.025
STD	19.1	20	0.9	0.421	0.028
	20	20.75	0.75	0.181	0.011
	20.75	21.3	0.55	0.228	0.019
	21.3	21.76	0.46	0.297	0.022
	21.76	22.45	0.69	0.162	0.01

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0070	2.8	3.7	0.9	0.005	0.002
	3.7	4.5	0.8	<0.005	0.002
	4.5	5.3	0.8	<0.005	0.002
	5.3	6	0.7	<0.005	<0.001
	6	6.77	0.77	<0.005	<0.001
	6.8	7.5	0.7	<0.005	0.001
	7.5	8.28	0.78	0.014	0.001
	8.28	9	0.72	<0.005	<0.001
	9	10.15	1.15	<0.005	<0.001
	10.15	11.1	0.95	<0.005	<0.001
	11.1	12.25	1.15	0.008	<0.001
	12.3	12.9	0.6	0.175	0.002
	12.9	14	1.1	0.377	0.019
	14	15	1	0.372	0.015
	15	16.15	1.15	0.533	0.044
	16.15	17.42	1.27	0.671	0.085
	17.42	17.85	0.43	0.997	0.055
	17.85	19	1.15	1.26	0.05
	19	19.35	0.35	1.07	0.088
	19.35	20.3	0.95	0.749	0.038
	20.3	20.7	0.4	0.856	0.093
	20.7	21.2	0.5	1.39	0.17
	21.2	22.2	1	1.25	0.12
	22.2	23	0.8	1.5	0.164
	23	24.07	1.07	0.76	0.096
	24.07	25.2	1.13	0.747	0.129
	25.2	26	0.8	0.677	0.105
	26	27	1	0.939	0.115
	27	28	1	0.406	0.029
	28	29.2	1.2	1.48	0.061
	29.2	29.8	0.6	1.5	0.016
	29.8	30.72	0.92	2.37	0.017
STD	30.72	31.5	0.78	0.556	0.01
	31.85	32.48	0.63	0.297	0.01
	33.25	33.5	0.25	0.871	0.017
	34.05	34.85	0.8	0.678	0.098
	34.85	35.75	0.9	1.28	0.029
	36.05	37.2	1.15	0.689	0.04
	37.2	38.25	1.05	1.47	0.023
	39.55	40.5	0.95	1.25	0.034
	40.5	40.85	0.35	0.657	0.018

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0101	0.6	1.6	1	0.311	0.017
	1.6	2.4	0.8	1.02	0.045
	2.4	3	0.6	1.55	0.107
	3	3.7	0.7	1.06	0.074
	3.7	4.9	1.2	1.32	0.046
	4.9	6.2	1.3	1.21	0.028
	6.2	7	0.8	0.713	0.02
	7	8	1	0.627	0.018
	8	9	1	0.29	0.014
	9	9.85	0.85	0.342	0.015
	9.85	10.9	1.05	0.283	0.011
	10.9	11.45	0.55	0.523	0.021
	11.45	12.5	1.05	0.265	0.013
	12.5	13.2	0.7	0.143	0.01
	13.2	13.7	0.5	0.153	0.012
	13.7	14.75	1.05	0.119	0.01
	14.75	15.4	0.65	0.134	0.014
	15.4	16.15	0.75	0.076	0.009
	16.15	17.2	1.05	0.165	0.014
	17.2	17.75	0.55	0.336	0.019
	17.75	18.7	0.95	0.227	0.012
	18.7	19.6	0.9	0.171	0.012

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0085A	2.95	3.6	0.65	0.016	0.001
	3.6	4.6	1	0.009	0.001
	4.6	5.6	1	<0.005	<0.001
	5.6	6.8	1.2	0.023	<0.001
	6.8	7.4	0.6	0.068	0.003
	7.4	8.1	0.7	0.325	0.012
	8.1	8.85	0.75	0.667	0.019
	8.85	9.6	0.75	1.03	0.023
	9.6	10.1	0.5	0.986	0.032
	10.1	11.1	1	0.735	0.022
	11.1	12	0.9	0.481	0.009
	12	13.17	1.17	0.224	0.007
	13.17	14.4	1.23	0.578	0.038
	14.4	15.3	0.9	0.255	0.035
	15.3	16	0.7	0.249	0.05
	16	17.1	1.1	0.328	0.044
	17.1	17.75	0.65	0.387	0.024
	17.75	18.6	0.85	0.558	0.025
	18.6	19	0.4	0.59	0.027
	19	20	1	0.612	0.038
	20	21.1	1.1	0.449	0.01
	21.1	21.6	0.5	1.03	0.035
	21.6	22.6	1	1.04	0.032
	22.6	23.3	0.7	0.665	0.017
	23.3	23.9	0.6	0.615	0.012
	23.9	24.8	0.9	0.802	0.021
	25.2	25.9	0.7	0.688	0.022
	25.9	26.5	0.6	0.652	0.028
	26.5	27.5	1	0.43	0.016
	27.5	28.65	1.15	0.438	0.023
	28.65	29.2	0.55	0.231	0.01
	29.2	30.2	1	0.266	0.021
	30.4	30.9	0.5	0.252	0.012
	30.9	31.6	0.7	0.265	0.012
STD	31.6	32.1	0.5	0.282	0.01
	32.1	32.7	0.6	0.244	0.01
	32.7	33.15	0.45	0.247	0.008

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0094	2.8	3.6	0.8	<0.005	<0.001
	3.8	5.05	1.25	<0.005	<0.001
	5.05	5.25	0.2	<0.005	<0.001
	5.25	6.25	1	0.071	0.001
	6.25	7.25	1	0.16	0.036
	7.25	7.5	0.25	0.233	0.05
	7.5	8.72	1.22	0.247	0.031
	8.72	8.92	0.2	0.241	0.048
	8.92	10.06	1.14	0.507	0.024
	10.1	11.1	1	0.478	0.008
	11.1	11.83	0.73	0.236	0.026
	12.1	13.1	1	0.509	0.08
	13.1	13.96	0.86	0.272	0.048
	13.96	15	1.04	0.163	0.023
	15	15.9	0.9	0.172	0.018
	15.9	16.6	0.7	0.618	0.035
	16.6	17.53	0.93	0.383	0.05
	17.6	18.75	1.15	0.193	0.073
	18.75	19.9	1.15	0.608	0.052
	19.9	20.15	0.25	0.796	0.009
	20.15	21.3	1.15	0.733	0.026
	21.4	22.6	1.2	0.758	0.033
	22.6	23.94	1.34	0.854	0.038
	24.1	25	0.9	0.966	0.11
	25	26	1	1.03	0.103
	26	27	1	0.97	0.089
	27	28.05	1.05	1.04	0.08
	28.05	28.92	0.87	0.845	0.092
	28.92	30.03	1.11	0.795	0.124
STD	30.1	31.16	1.06	0.992	0.12
	31.16	31.95	0.79	0.318	0.049
	31.95	33.1	1.15	0.876	0.079
	33.1	34	0.9	0.772	0.123
	34	35.28	1.28	0.852	0.088
	35.28	35.9	0.62	0.386	0.083
	35.9	36.82	0.92	0.848	0.136
	38	39	1	0.604	0.074
	39	40	1	0.284	0.044
	40	41	1	0.377	0.05
	41	42.2	1.2	0.468	0.064

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0108	1.12	2.14	1.02	0.618	0.076
	3.8	4.6	0.8	0.398	0.013
	4.6	5.4	0.8	0.395	0.039
	5.4	6.4	1	1.1	0.09
	6.4	7.5	1.1	1.37	0.071
	7.5	8.1	0.6	0.26	0.01
	8.2	8.9	0.7	0.27	0.009
	8.9	9.9	1	1.14	0.03
	9.9	10.6	0.7	1.03	0.023
	10.6	11.2	0.6	1.44	0.03
	11.2	12.2	1	1.45	0.025
STD	12.2	12.92	0.72	0.835	0.017
	12.92	13.5	0.58	0.635	0.012
	13.5	14.22	0.72	0.677	0.011
	14.22	14.5	0.28	0.939	0.016
	14.5	14.9	0.4	0.819	0.013
	14.9	15.2	0.3	0.586	0.01
	15.2	15.65	0.45	1.1	0.018
	15.65	15.9	0.25	0.422	0.011
	15.9	17.05	1.15	0.901	0.021
	17.05	17.86	0.81	1.35	0.023
	18	18.45	0.45	0.765	0.015
	18.45	19.7	1.25	0.274	0.01

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0121A	2.88	3.75	0.87	0.032	0.001
	3.75	5	1.25	0.063	0.002
	5	5.95	0.95	<0.005	<0.001
	5.95	6.75	0.8	<0.005	<0.001
	6.75	7.5	0.75	0.083	0.007
	7.5	8.45	0.95	0.333	0.022
	8.45	9.44	0.99	0.796	0.036
	9.44	10.25	0.81	0.821	0.027
	10.25	11	0.75	1.02	0.023
	11	11.7	0.7	0.947	0.025
	11.7	12.6	0.9	0.817	0.02
	12.6	13.56	0.96	0.821	0.104
	13.56	14.25	0.69	1.08	0.228
	14.25	15	0.75	0.923	0.034
	15	15.75	0.75	1.78	0.099
	15.75	16.32	0.57	2.34	0.365
	16.32	17.25	0.93	1.93	0.198
	17.25	17.92	0.67	1.09	0.13
	17.92	18.7	0.78	1.79	0.119
	18.7	19.37	0.67	0.308	0.012
	19.37	19.66	0.29	1	0.078
	19.66	20.87	1.21	1.38	0.141
	20.87	21.5	0.63	1.71	0.068
	21.75	22.34	0.59	0.336	0.011
	22.34	22.71	0.37	1.34	0.029
	23.25	23.85	0.6	1.86	0.026

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0114	0.4	1.3	0.9	0.128	0.005
	1.3	2	0.7	0.281	0.011
	2	2.95	0.95	0.255	0.003
	2.95	3.2	0.25	0.843	0.029
	3.2	4.35	1.15	0.67	0.052
	4.6	5.11	0.51	0.646	0.034
	5.11	6	0.89	0.675	0.084
	6	7.35	1.35	0.726	0.035
	7.35	7.55	0.2	0.763	0.12
	7.55	8.33	0.78	0.608	0.214
	8.33	9.56	1.23	1.29	0.283
	9.56	10.24	0.68	0.874	0.117
	10.24	11	0.76	0.905	0.091
STD	11	11.8	0.8	1.3	0.018
	11.8	12.84	1.04	1.01	0.167
	13.1	14.18	1.08	0.883	0.106
	14.4	15.39	0.99	1.15	0.084
	15.39	16.25	0.86	2.15	0.04
	16.25	16.5	0.25	1.75	0.046
	16.5	17.05	0.55	1.55	0.024
	17.05	18.3	1.25	1.74	0.031
	18.3	18.84	0.54	1.53	0.021
	18.84	19.04	0.2	2.19	0.029
	19.04	19.5	0.46	1.88	0.031
	19.5	20.2	0.7	1.51	0.04
	20.2	21	0.8	1.85	0.025
	21	21.67	0.67	0.697	0.017
	21.7	24.55	2.85	0.626	0.011
	24.55	25.36	0.81	1.04	0.016
	26.05	27.55	1.5	0.8	0.031
	27.55	28.45	0.9	0.867	0.02
	28.45	29.35	0.9	0.6	0.028
	29.35	30.22	0.87	0.792	0.015
	30.22	31.49	1.27	0.7	0.038
	31.55	32.05	0.5	0.368	0.012
	32.05	32.75	0.7	1.33	0.023
	32.75	33.6	0.85	1.09	0.02
	33.6	34.45	0.85	0.545	0.013
	34.65	35.85	1.2	0.714	0.024
	35.85	36.89	1.04	0.284	0.011