

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0057	0.55	0.7	0.15		
	5.05	5.3	0.25		
	8.15	8.4	0.25		
	11.35	12.15	0.8	0.097	0.003
	12.15	12.4	0.25		
	12.4	13.5	1.1	0.193	0.012
	13.5	14.1	0.6	0.136	0.014
	14.1	14.65	0.55	0.264	0.009
	14.9	16	1.1	0.269	0.023
	16	17	1	0.36	0.024
	17	18	1	0.345	0.031
	18	19.25	1.25	0.474	0.029
	19.25	20.5	1.25	0.515	0.021
	20.5	21.55	1.05	0.871	0.026
	21.55	22.25	0.7	0.942	0.118
	22.25	23.25	1	0.605	0.073
	23.25	24.25	1	1.32	0.133
	24.25	25.25	1	1.21	0.153
	25.25	26.1	0.85	0.919	0.135
	26.1	26.35	0.25		
	26.35	26.8	0.45	1.41	0.141
	27.4	27.8	0.4	1.54	0.047
	27.8	28.1	0.3	0.58	0.013
	28.1	28.7	0.6	1.6	0.023
	28.7	29.7	1	0.267	0.011

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0058A	STD				
	6.8	7.55	0.75	0.009	<0.001
	7.55	8.7	1.15	0.052	0.005
	8.7	9.55	0.85	0.151	0.008
	9.55	10.5	0.95	0.428	0.014
	10.5	11.5	1	0.561	0.058
	11.5	12.6	1.1	0.637	0.049
	12.6	13.8	1.2	0.688	0.083
	13.8	14.6	0.8	0.784	0.275
	14.6	15.4	0.8	1.32	0.255
	15.4	16.15	0.75	1.98	0.077
	16.15	17.5	1.35	0.617	0.012
	17.5	18.2	0.7	1.45	0.051
	18.2	19.2	1	1.03	0.05
	19.2	20.25	1.05	0.346	0.019
	20.25	21.3	1.05	0.957	0.026
	22	22.5	0.5	0.521	0.079
	22.5	23.5	1	1.34	0.066
	23.5	24.6	1.1	1.48	0.068
	24.6	25.5	0.9	1.03	0.029
	25.5	26	0.5	0.818	0.024
	26	27.21	1.21	0.336	0.011

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0028	5.4	6.4	1	0.033	0.001
	6.4	7.54	1.14	0.528	0.046
	7.54	9	1.46	0.749	0.104
	9	10	1	0.709	0.063
	10	11.47	1.47	1.11	0.042
	11.47	13	1.53	1.11	0.074
	13	14	1	0.897	0.05
	14	15.42	1.42	0.913	0.09
	15.42	16.4	0.98	1.09	0.139
	16.4	17.4	1	1.02	0.123
	17.4	18	0.6	1.01	0.257
	18	18.66	0.66	0.603	0.099
	18.66	19.4	0.74	0.648	0.057
	19.4	20.4	1	1.07	0.089
	20.4	21.73	1.33	1.05	0.119
	21.73	22.6	0.87	0.725	0.093
	22.6	23.53	0.93	1.21	0.178
	23.53	25	1.47	0.709	0.13
	25	25.67	0.67	0.965	0.292
	25.67	26.67	1	1.01	0.116
	26.67	27.5	0.83	0.786	0.167
	27.5	27.9	0.4	0.645	0.124
	27.9	29	1.1	0.597	0.126
	29	29.8	0.8	0.705	0.197
	29.8	30.73	0.93	1.21	0.091
	30.73	32	1.27	1.27	0.028
	32	32.7	0.7	0.972	0.019
	32.7	34	1.3	0.378	0.011
	STD				

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0029	3.8	4.32	0.52	0.018	0.004
	4.4	5.37	0.97	0.17	0.006
	5.37	6.1	0.73	0.239	0.019
	6.1	6.9	0.8	0.284	0.01
	7.2	8	0.8	0.611	0.046
	8	8.82	0.82	0.715	0.058
	9.2	10.4	1.2	0.793	0.073
	10.4	11.6	1.2	0.764	0.092
	11.6	12.8	1.2	0.99	0.115
	12.8	13.8	1	0.771	0.069
	13.8	14.87	1.07	0.979	0.08
	14.87	15.94	1.07	0.99	0.093
	16	16.6	0.6	0.951	0.094
	16.6	17.5	0.9	0.448	0.011
	17.5	18.2	0.7	1.24	0.088
	18.2	19.04	0.84	1.7	0.06
	19.4	20.58	1.18	1.59	0.098
	20.9	22.1	1.2	1.34	0.033
	22.1	23.1	1	1.09	0.038
	23.3	24.2	0.9	1.12	0.039
	24.8	25.2	0.4	0.348	0.012
	25.2	26.4	1.2	1.23	0.032
	26.4	27.3	0.9	0.382	0.011

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0049	4	5.25	1.25	0.02	0.002
	5.25	6.5	1.25	0.028	<0.001
	6.5	7.75	1.25	0.301	0.011
	7.75	9	1.25	0.208	0.008
	9	10.25	1.25	0.301	0.02
	10.25	11.5	1.25	0.36	0.028
	11.5	12.75	1.25	0.377	0.037
	12.75	14	1.25	0.313	0.054
	14	15	1	0.348	0.056
	15	15.9	0.9	0.876	0.09
	15.9	16.75	0.85	1.29	0.075
	16.85	17.35	0.5	1.99	0.04
	17.35	18.45	1.1	1.5	0.037
	18.45	18.9	0.45	1.61	0.013
	18.9	19.8	0.9	1.07	0.062
	19.8	20.7	0.9	1.11	0.068
	20.7	21.7	1	1.09	0.065
	21.7	22.72	1.02	0.817	0.044
	24.8	25.3	0.5	0.149	0.009
	25.3	25.6	0.3	0.506	0.018
	25.6	26.1	0.5	0.189	0.009
	26.1	26.5	0.4	0.468	0.019
	26.5	27.5	1	0.543	0.054
	27.5	27.95	0.45	0.749	0.012
	27.95	28.45	0.5	1.46	0.022
	28.45	29.45	1	0.287	0.022
	29.45	29.9	0.45	0.375	0.02
	29.9	30.75	0.85	0.266	0.011
	30.75	31.75	1	0.259	0.012
	32.65	33.65	1	0.253	0.011

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0027	4	5.25	1.25	0.051	<0.001
	5.25	6.5	1.25	0.065	0.003
	6.5	7.75	1.25	0.576	0.009
	7.75	9	1.25	0.577	0.031
	9	10.25	1.25	0.577	0.044
	10.25	11.5	1.25	0.798	0.045
	11.5	12.75	1.25	1.06	0.052
	12.75	14	1.25	0.965	0.053
	14	15.25	1.25	0.874	0.075
	15.25	16.4	1.15	1	0.158
	16.4	17.65	1.25	1.04	0.084
	17.65	18.55	0.9	0.917	0.107
	18.55	19.4	0.85	0.784	0.177
	19.4	20.4	1		
	20.4	21.65	1.25	0.92	0.117
	21.65	22.9	1.25	1.23	0.284
	22.9	24.15	1.25	1.04	0.147
	24.15	25.4	1.25	0.886	0.086
	25.4	26.65	1.25	0.732	0.134
	26.65	27.9	1.25	0.781	0.135
	27.9	29.15	1.25	1.2	0.139
	29.15	30.4	1.25	1.1	0.133
	30.4	31.65	1.25	0.956	0.095
	31.65	32.95	1.3	0.939	0.115
	32.95	34	1.05	1.41	0.113
	34	35.1	1.1	1.64	0.08
	35.1	35.82	0.72	0.342	0.012
	36	37.25	1.25	1.27	0.073
	37.25	38.5	1.25	1.33	0.052
	38.5	39.75	1.25	0.322	0.013

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0030	5	6	1	0.175	0.009
	6	7	1	0.302	0.045
	7	7.7	0.7	0.498	0.105
	7.7	8.95	1.25	0.233	0.01

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0061	4	5.25	1.25	0.802	0.07
	5.25	6.5	1.25	1.17	0.105
	6.5	7.75	1.25	1.13	0.081
	7.75	9	1.25	1.04	0.137
	9	10.25	1.25	1.15	0.043
	10.25	11.5	1.25	1.31	0.068
	11.5	12.75	1.25	0.988	0.188
	12.75	14	1.25	1.08	0.091
	14	15.25	1.25	0.97	0.06
	15.25	16.5	1.25	1.23	0.064
	16.5	17.75	1.25	1.05	0.058
	17.75	19	1.25	0.954	0.066
	19	20.25	1.25	1.02	0.153
	20.25	21.5	1.25	1.24	0.205
	21.5	22.75	1.25	1.11	0.113
	22.75	24	1.25	1.14	0.226
	24	25	1	0.76	0.143
	25	26	1	0.762	0.205
	26	26.9	0.9	0.796	0.232
	26.9	28.15	1.25	0.478	0.017
	28.15	29.4	1.25	0.341	0.013
	STD				

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0063	3.4	4.65	1.25	0.977	0.115
	4.65	5.86	1.21	1.09	0.21
	6.1	7.35	1.25	0.908	0.188
	7.35	8.6	1.25	0.648	0.101
	8.6	9.6	1	0.559	0.062
	9.6	10.53	0.93	0.717	0.019
	10.9	11.88	0.98	0.696	0.016
	11.95	12.55	0.6	0.744	0.015
	12.55	14.05	1.5	0.524	0.014
	15.1	15.62	0.52	0.339	0.011
	16.3	17.65	1.35	1.09	0.019
	17.65	18.35	0.7	2.07	0.044
	18.35	19.4	1.05	0.633	0.016
	19.4	20.58	1.18	0.625	0.014
	20.65	21.4	0.75	0.937	0.015
	21.4	22.95	1.55	0.385	0.011

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0062	0.9	1.5	0.6	0.139	0.005
	1.7	2.7	1	0.323	0.033
	2.7	3.7	1	0.469	0.09
	3.7	4.36	0.66	0.586	0.109
	4.36	5	0.64	0.523	0.097
	5	6	1	0.906	0.1
	6	7.3	1.3	0.722	0.066
	7.3	7.75	0.45	0.884	0.081
	7.75	8.4	0.65	0.387	0.018
	8.4	9.1	0.7	0.691	0.049
	9.1	10.4	1.3	0.261	0.013

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0072	4.6	5.75	1.15	0.345	0.051
	5.75	6.2	0.45	1.09	0.043
	6.3	7.3	1	1.1	0.044
	7.3	8.3	1	0.939	0.044
	8.3	9	0.7	0.689	0.054
	9	10	1	0.711	0.024
	10	11	1	1.09	0.03
	11	11.9	0.9	1.21	0.23
	11.9	13.06	1.16	0.689	0.092
	13.3	14.65	1.35	0.805	0.026
	14.65	15.1	0.45	0.601	0.056
	15.1	16	0.9	1.03	0.143
	16	16.7	0.7	0.459	0.064
	16.7	17.6	0.9	0.861	0.06
	17.6	18.75	1.15	0.91	0.13
	18.75	20.04	1.29	1.52	0.154
	20.1	21.05	0.95	1.58	0.188
	STD				
	21.1	22	0.9	1.24	0.186
	22	23	1	0.655	0.034
	23	23.7	0.7	0.467	0.016
	23.7	24.7	1	0.39	0.019
	24.7	25.85	1.15	0.369	0.018
	25.85	26.73	0.88	1.83	0.044
	26.73	27.2	0.47	1.69	0.027
	27.4	28.4	1	2.27	0.029
	28.4	29	0.6	0.413	0.013
	29	30.05	1.05	0.965	0.022
	30.1	31.46	1.36	0.743	0.035
	31.6	32.8	1.2	0.584	0.024
	32.8	33.54	0.74	0.336	0.011

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0050	5	6.25	1.25	0.397	0.006
	6.25	7.5	1.25	0.752	0.014
	7.5	8.75	1.25	0.613	0.038
	8.75	10	1.25	0.214	0.063
	10	10.6	0.6	1.02	0.037
	10.6	11	0.4	1.38	0.045
	11	12.25	1.25	1.01	0.039
	12.25	13.5	1.25	0.847	0.038
	13.5	14.75	1.25	0.674	0.026

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0059	3.68	4.18	0.5	0.007	0.003
	4.18	5	0.82	0.062	0.003
	5	5.6	0.6	0.343	0.06
	5.6	6.54	0.94	0.587	0.117
	6.54	7.7	1.16	0.637	0.262
	7.7	8.74	1.04	0.8	0.097
	8.74	9.6	0.86	0.907	0.073

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0081	3.3	4.5	1.2	0.006	0.002
	4.6	5.8	1.2	0.047	0.001