

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co	
MAM-KK-0064	0.7	1.3	0.6	0.645	0.085	
	1.3	2	0.7	0.98	0.072	
	2	2.56	0.56	1.19	0.047	
	2.8	3.72	0.92	0.717	0.09	
	3.8	4.64	0.84	0.332	0.044	
	4.64	5.05	0.41	0.348	0.015	
	5.05	5.3	0.25	0.36	0.007	
	5.3	6.3	1	0.331	0.029	
	6.3	7	0.7	0.737	0.058	
	7	8	1	1.11	0.044	
	8	8.85	0.85	1.31	0.027	
	8.85	9.1	0.25	0.645	0.064	
	STD	9.1	10	0.9	1.11	0.056
		10	11	1	1.16	0.061
11		12.25	1.25	1.28	0.062	
12.25		13.07	0.82	1.1	0.115	
13.07		14	0.93	1.16	0.09	
14		14.76	0.76	1.08	0.135	
14.76		15.71	0.95	1.3	0.159	
15.71		16.6	0.89	1.17	0.109	
16.6		17.2	0.6	1.31	0.073	
17.2		17.9	0.7	1.51	0.025	
17.9		18.35	0.45	0.836	0.016	
18.35		18.9	0.55	1.44	0.036	
18.9		19.8	0.9	1.42	0.037	
19.8		20.19	0.39	0.672	0.012	
20.19		21.1	0.91	0.355	0.012	
21.1		22	0.9	0.462	0.014	
22		23	1	0.25	0.014	
23.58		24	0.42	0.845	0.017	
24		24.7	0.7	0.451	0.015	
24.7		25.3	0.6	0.491	0.018	
25.44		26.5	1.06	0.34	0.014	
26.5		27.38	0.88	0.259	0.011	
27.5		28.37	0.87	0.262	0.012	
28.5		29.05	0.55	0.304	0.012	
29.05		29.84	0.79	0.225	0.012	
30.1		30.92	0.82	0.185	0.011	
31.7		32.85	1.15	0.521	0.016	
32.83		33	0.17	0.673	0.014	
33		33.85	0.85	0.574	0.019	
33.89		35.4	1.51	0.253	0.012	

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0081	3.3	4.5	1.2	0.006	0.002
	4.6	5.8	1.2	0.047	0.001
	5.8	7.25	1.45	0.305	0.018
	7.25	8.5	1.25	0.385	0.069
	8.5	9.62	1.12	0.628	0.093
	9.8	11	1.2	0.548	0.101
	11	12.25	1.25	0.603	0.186
	12.25	13.5	1.25	0.833	0.296
	13.5	14.75	1.25	0.789	0.286
	14.75	15.9	1.15	0.786	0.085
	15.9	16.6	0.7	0.77	0.273
	16.6	17.1	0.5	0.735	0.197
	17.1	18.3	1.2	0.698	0.244
	18.3	19.1	0.8	0.881	0.091
	19.1	20	0.9	0.791	0.021
	20	21.3	1.3	0.455	0.011
	21.3	22.45	1.15	0.531	0.023
	22.45	23.7	1.25	0.338	0.017
	23.7	24.95	1.25	0.292	0.011

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0065	5	6.25	1.25	0.009	0.001
	6.25	7.25	1	0.076	0.002
	7.25	8.05	0.8	0.415	0.008
	8.05	8.3	0.25	0.715	0.037
	8.3	9.5	1.2	0.646	0.036
	9.5	10.7	1.2	1.03	0.078
	10.7	11.75	1.05	1.14	0.068
	11.75	12	0.25	0.925	0.032
	12	13.3	1.3	1.02	0.159
	13.3	14.55	1.25	0.866	0.202
	14.55	15.85	1.3	1.37	0.162
	15.85	16.45	0.6	1.77	0.074
	16.45	17.1	0.65	1.06	0.024
	17.1	17.3	0.2	1.16	0.032
	17.3	17.9	0.6	1.77	0.039
	17.9	18.1	0.2	1.38	0.042
	18.1	18.6	0.5	0.568	0.015
	18.6	19	0.4	0.724	0.015
	19	19.72	0.72	0.612	0.015
	19.95	20.8	0.85	0.629	0.017
	20.8	21.75	0.95	1.29	0.017
	21.75	21.95	0.2	1.89	0.043
	21.95	23	1.05	1.05	0.018
	23	24.1	1.1	1.11	0.016
	24.1	24.7	0.6	0.685	0.014
	24.7	25.8	1.1	0.729	0.018
	25.8	26.55	0.75	0.61	0.012
	26.55	26.9	0.35	1.62	0.026
	26.9	27.7	0.8	0.511	0.013
	27.7	28.5	0.8	0.388	0.012
	28.9	29.4	0.5	0.82	0.025
	29.4	29.8	0.4	0.646	0.03
	29.8	30.5	0.7	0.493	0.016
30.5	31.75	1.25	0.27	0.013	
STD					

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0082	3.3	4.25	0.95	<0.005	<0.001
	4.25	5.5	1.25	<0.005	<0.001
	5.5	6.75	1.25	0.077	0.003
	6.75	8	1.25	0.419	0.011
	8	9.25	1.25	0.543	0.01
	9.25	10.5	1.25	0.527	0.013
	10.5	11.75	1.25	0.408	0.029
	11.75	13	1.25	0.424	0.504
	13	14.25	1.25	0.245	0.449
	14.25	15.5	1.25	0.221	0.35
	15.5	16.75	1.25	0.365	0.12
	16.75	18	1.25	0.433	0.08
	18	19.25	1.25	0.537	0.088
	19.25	20.5	1.25	0.641	0.139
	20.5	21.75	1.25	0.526	0.108
	21.75	23	1.25	0.421	0.088
	23	23.6	0.6	0.531	0.061
	23.6	24.8	1.2	0.318	0.013
	24.8	26.05	1.25	0.313	0.012

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0060	5	6.25	1.25	0.083	0.006
	6.25	7.5	1.25	0.764	0.071
	7.5	8.75	1.25	1.16	0.21
	8.75	10	1.25	1.08	0.072
	10	11.25	1.25	0.966	0.047
	11.25	12.5	1.25	1.14	0.053
	12.5	13.75	1.25	1.23	0.274
	13.75	15	1.25	0.941	0.023
	15	16.25	1.25	0.833	0.177
	16.25	17.5	1.25	0.938	0.166
	17.5	18.75	1.25	0.615	0.066
	18.75	20	1.25	0.937	0.243
	20	21.25	1.25	0.985	0.132
	21.25	22.5	1.25	1.51	0.182
	22.5	23.15	0.65	1.43	0.2
	23.3	24.1	0.8	1.67	0.137
	24.1	24.95	0.85	1.91	0.049
	24.95	25.6	0.65	1.28	0.06
	25.6	26.8	1.2	0.661	0.021
	26.8	27.45	0.65	0.677	0.023
	27.8	29	1.2	0.365	0.067
	29	29.85	0.85	0.967	0.068
	29.85	30.7	0.85	0.763	0.046

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0048	2.45	3.7	1.25	0.031	0.013
	3.7	4.6	0.9	0.336	0.078
	4.6	5.3	0.7	0.139	0.01
	5.3	6.55	1.25	0.189	0.011
STD					

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0073	3.6	4.14	0.54	0.02	0.003
	4.6	5.8	1.2	0.31	0.009
	6.1	7.11	1.01	0.482	0.041
	7.11	8	0.89	0.619	0.024
	8	8.54	0.54	0.765	0.013
	8.6	9.5	0.9	0.748	0.012
	9.5	10.2	0.7	0.771	0.029
	10.2	11.31	1.11	0.905	0.076
	11.31	12.2	0.89	0.667	0.061
	12.2	13.47	1.27	1.08	0.136
STD					

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0073	13.47	14.11	0.64	1.74	0.088
	14.11	14.81	0.7	1.55	0.024
	14.81	15.52	0.71	1.48	0.018
	15.52	16.52	1	0.388	0.011
	16.52	17.7	1.18	2.67	0.035
	17.7	18.7	1	1.76	0.037
	18.7	19.64	0.94	2.25	0.032
	19.7	20.35	0.65	1.71	0.043
	20.35	21.06	0.71	0.486	0.013
	21.06	21.7	0.64	1.4	0.037
	22	23	1	0.422	0.03
	23	24.28	1.28	1.16	0.037
	24.28	25.2	0.92	0.4	0.012
	25.2	25.65	0.45	1.05	0.015
	25.65	26	0.35	0.355	0.011
	28	28.57	0.57	0.387	0.011
	28.7	29.25	0.55	0.591	0.018
	29.25	30.25	1	0.221	0.01



Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0066	1.65	2	0.35	0.075	0.01
	2.07	3.1	1.03	0.016	0.003
	3.1	3.8	0.7	0.032	0.002
	4.05	4.6	0.55	0.2	0.011
	4.7	5.3	0.6	0.186	0.011
	5.4	6.35	0.95	0.238	0.019
	6.35	7	0.65	0.814	0.089
	7	8.07	1.07	0.54	0.047
	8.07	9.04	0.97	0.963	0.078
	9.04	9.6	0.56	0.98	0.029
	9.6	10.6	1	0.697	0.016
	10.6	11	0.4	0.607	0.015
	11	11.58	0.58	0.77	0.03
	11.58	11.86	0.28	0.536	0.013
	12.07	12.6	0.53	0.652	0.015
	12.6	13.22	0.62	1.06	0.044
	13.22	14.4	1.18	0.724	0.019
	14.4	14.9	0.5	0.4	0.013
	14.9	15.88	0.98	0.402	0.017
	15.88	16.5	0.62	0.31	0.014
	16.5	17.23	0.73	0.329	0.013
	17.23	18	0.77	0.263	0.012
	18	18.7	0.7	0.303	0.012
18.7	19.22	0.52	0.313	0.014	
19.22	20.31	1.09	0.315	0.012	
20.5	20.8	0.3	0.228	0.011	
20.8	21.3	0.5	0.46	0.013	
21.3	21.9	0.6	0.086	0.007	
21.9	22.3	0.4	0.3	0.006	
22.3	23.4	1.1	0.177	0.008	
23.4	24	0.6	0.116	0.009	
STD	24	24.4	0.4	0.205	0.007

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0083	1.15	1.5	0.35	0.011	0.003
	1.5	2.6	1.1	0.515	0.036
	2.6	3.2	0.6	0.648	0.062
	3.2	3.87	0.67	0.812	0.078
	3.9	5.16	1.26	0.708	0.126
	5.16	5.8	0.64	0.649	0.144
	5.8	6.94	1.14	0.621	0.125
	6.94	8	1.06	0.728	0.101
	8	8.6	0.6	0.654	0.054
	8.8	9.06	0.26	0.317	0.012
	9.1	9.4	0.3	0.556	0.02
	9.4	10.5	1.1	0.374	0.011
	10.5	11.65	1.15	0.267	0.01
	11.65	11.95	0.3	0.229	0.016
	11.95	12.5	0.55	0.249	0.011
	14.5	15.1	0.6	0.255	0.011
	15.2	15.8	0.6	0.353	0.014

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0074	4	5.25	1.25	0.567	0.017
	5.25	6.5	1.25	1.06	0.018
	6.5	7.75	1.25	0.769	0.029
	7.75	9	1.25	0.951	0.028
	9	10.25	1.25	0.86	0.076
	10.25	11.5	1.25	0.87	0.12
	11.5	12.75	1.25	0.741	0.057
	12.75	14	1.25	0.443	0.065
	14	15.25	1.25	0.464	0.077
	15.25	16.5	1.25	0.803	0.115
	16.5	17.75	1.25	0.656	0.087
	17.75	18.75	1	1.14	0.098
	18.75	19.75	1	1.08	0.237
	19.75	20.75	1	1.56	0.365
	20.75	21.45	0.7	1.69	0.223
	21.45	22.55	1.1	1.65	0.074
	22.55	23.6	1.05	0.466	0.056
	23.6	24.65	1.05	0.48	0.08
	24.65	25.65	1	1.34	0.127
	25.65	26.65	1	2.38	0.099
	26.65	27.04	0.39	1.6	0.058
	27.3	27.8	0.5	2.12	0.292
	27.8	28.5	0.7	0.404	0.05
	28.5	29.9	1.4	0.449	0.074
	29.9	30.4	0.5	0.666	0.146

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0091	3.2	4.12	0.92	0.174	0.005
	4.12	4.37	0.25	0.409	0.016
	4.37	5.6	1.23	0.647	0.047
	5.6	6.69	1.09	0.889	0.05
	6.69	6.94	0.25	0.983	0.058
	6.94	7.9	0.96	0.969	0.044
	7.9	8.7	0.8	0.943	0.044
	8.7	9.6	0.9	0.613	0.102
	9.6	10.6	1	0.932	0.157
	10.6	11.34	0.74	1.04	0.185
	11.34	11.59	0.25	0.946	0.172
	11.59	12.6	1.01	1.03	0.364
	12.6	13.4	0.8	1.29	0.188
	13.4	14.5	1.1	0.98	0.172
	14.5	15.8	1.3	1.07	0.104
	15.8	16.7	0.9	1.22	0.143
	16.7	17.26	0.56	1.8	0.067
	17.26	17.51	0.25	2.14	0.067
	17.51	18.3	0.79	1.36	0.033
	18.3	19.3	1	0.293	0.012
STD					

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0074A	2	3.1	1.1	0.028	0.002
	3.1	4.2	1.1		
	4.2	5.1	0.9	0.017	0.002
	5.2	6.4	1.2	<0.005	0.001
	6.4	7.4	1	0.108	0.002
	7.4	8.07	0.67	0.21	0.005
	8.07	8.6	0.53	0.423	0.011
	8.6	9.45	0.85	0.353	0.016
	9.45	9.9	0.45	0.426	0.012
	9.9	11.2	1.3	0.446	0.009
	11.2	12	0.8	0.49	0.044
	12	12.8	0.8	0.96	0.018
	12.8	13.5	0.7	0.447	0.054
	13.5	14.4	0.9	0.471	0.035
	14.4	15.2	0.8	0.63	0.18
	15.2	16.45	1.25	0.872	0.086
	16.45	16.7	0.25	1.36	0.086
	16.7	17.6	0.9	1.2	0.051
	17.6	18.1	0.5	1	0.051
	18.1	19	0.9	0.385	0.052
	19	20.1	1.1	0.412	0.044
	21.3	22.5	1.2	0.346	0.054
	22.5	23.41	0.91	0.351	0.054
	23.41	24.6	1.19	0.539	0.07
	24.6	24.85	0.25	1.03	0.065
	24.85	26	1.15	0.824	0.066
	26	26.5	0.5	0.785	0.124
	26.5	27.5	1	0.383	0.055
	27.5	28.55	1.05	0.546	0.056
	28.55	29	0.45	0.843	0.079
	29	30.32	1.32	1.1	0.164
	30.32	31.35	1.03	0.621	0.104
	31.35	32.15	0.8	0.759	0.087
	32.15	32.45	0.3	1.16	0.166
	32.45	32.7	0.25	1.01	0.12
32.7	34.05	1.35	0.844	0.126	
34.2	35.2	1	0.811	0.092	
35.2	36	0.8	1.73	0.11	
36	36.94	0.94	1.5	0.151	
37	38	1	0.912	0.089	
38	38.55	0.55	0.635	0.055	
STD					

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0067	3.3	4.33	1.03	0.011	0.002
	4.5	5.41	0.91	0.122	0.022
	5.45	6.51	1.06	0.408	0.079
	6.51	7.17	0.66	0.529	0.011
	7.17	8.29	1.12	0.821	0.031
	8.29	9	0.71	0.258	0.01
	9	10	1	0.54	0.013
	10	10.75	0.75	0.294	0.01
	10.75	11.6	0.85	0.332	0.011
	11.6	12.5	0.9	0.231	0.01
	12.5	13.15	0.65	0.245	0.009
	13.15	13.9	0.75	0.251	0.008
	13.9	14.6	0.7	0.273	0.009
	14.6	15.25	0.65	0.235	0.009
	15.25	16.05	0.8	0.225	0.009
	16.05	16.9	0.85	0.249	0.01
	16.9	17.2	0.3	0.233	0.01

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0084	0.7	1.5	0.8	0.007	0.002
	1.5	2.1	0.6	<0.005	0.002
	2.1	3.1	1	<0.005	0.002
	3.1	3.9	0.8	<0.005	<0.001
STD	3.9	4.59	0.69	<0.005	<0.001
	4.7	5.42	0.72	0.02	<0.001
	5.42	6.05	0.63	0.187	0.005
	6.05	7	0.95	0.569	0.025
	7	8.02	1.02	0.761	0.023
	8.1	8.98	0.88	0.923	0.02
	9	9.9	0.9	0.741	0.014
	9.9	10.6	0.7	1	0.078
	10.6	11.4	0.8	2.93	0.063
	11.4	12.15	0.75	1.74	0.049
	12.15	12.4	0.25	2.06	0.022
	12.4	13.57	1.17	1.39	0.09
	13.57	13.8	0.23	0.335	0.007
	13.8	14.2	0.4	0.235	0.009
	14.2	15.15	0.95	0.25	0.011
	15.15	16.1	0.95	0.241	0.008
	16.1	17.1	1	0.854	0.019
	17.1	18.3	1.2	0.485	0.015
	18.3	19.29	0.99	0.448	0.017
	19.4	20.6	1.2	0.464	0.015
	20.7	21.5	0.8	0.362	0.013
	21.5	22.1	0.6	0.267	0.01
22.1	22.45	0.35	1.1	0.042	
22.45	23.4	0.95	0.239	0.012	

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0092	0.6	1.7	1.1	0.01	0.002
	1.7	2.4	0.7	0.008	0.001
	2.4	3.3	0.9	<0.005	0.002
STD	3.3	4.53	1.23	0.083	0.004
	4.6	5.5	0.9	0.629	0.045
	5.5	6.8	1.3	0.543	0.067
	6.8	7.5	0.7	0.376	0.103
	7.5	8.3	0.8	0.715	0.286
	8.3	9	0.7	0.786	0.011
	9	10	1	0.83	0.012
	10	11	1	0.838	0.012
	11	12.37	1.37	0.675	0.012
	12.37	13.54	1.17	0.571	0.022
	13.6	14.2	0.6	0.84	0.017
	14.2	14.99	0.79	0.891	0.081
	15.1	16.1	1	0.958	0.011
	16.1	17.1	1	0.855	0.045
	17.1	18.1	1	0.7	0.023
	18.1	19	0.9	0.654	0.059
	19	19.54	0.54	0.673	0.074
	19.6	20.5	0.9	0.614	0.072
	20.5	21.07	0.57	0.672	0.118
	21.07	22.3	1.23	0.585	0.131
	22.3	23	0.7	0.815	0.083
	23	24	1	0.811	0.204
	24	25.32	1.32	1.58	0.237
	25.32	26.15	0.83	0.768	0.026
	26.15	26.6	0.45	0.377	0.017
	27.5	27.9	0.4	0.399	0.016
	27.9	28.7	0.8	1.22	0.098
	28.7	29.08	0.38	0.572	0.022
29.2	29.86	0.66	0.321	0.014	
30.5	31.35	0.85	0.9	0.023	
31.35	31.7	0.35	0.635	0.02	
31.7	32.97	1.27	0.247	0.013	



Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0069	2.44	3.5	1.06	0.732	0.076
	3.5	4.45	0.95	0.824	0.088
	4.45	5.45	1	0.821	0.048
	5.45	6.4	0.95	1.07	0.074
	6.4	7.5	1.1	1.24	0.072
	7.5	8.45	0.95	1.31	0.086
	8.45	9.25	0.8	0.98	0.062
	9.25	10.3	1.05	0.296	0.011
	10.3	10.95	0.65	1.6	0.035
	10.95	11.5	0.55	0.382	0.01
	11.5	12.3	0.8	1.18	0.029
	12.3	13.1	0.8	1.57	0.02
	13.1	13.7	0.6	0.37	0.011
	13.7	14.2	0.5	1.51	0.021
	14.2	15.3	1.1	0.39	0.016
	15.3	17.25	1.95	0.266	0.01
	17.25	18.2	0.95	0.71	0.014
	18.2	18.84	0.64	0.278	0.01

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0075	1.8	2.65	0.85	0.064	0.002
	2.65	3.58	0.93	0.215	0.014
	3.7	4.65	0.95	0.823	0.111
	4.65	5.35	0.7	0.3	0.013
	5.35	6	0.65	0.653	0.037
	6	7.04	1.04	0.692	0.035
	7.1	8.3	1.2	0.373	0.013
	8.3	9.45	1.15	0.902	0.051
	9.7	10.5	0.8	0.33	0.012
	10.5	11.78	1.28	1.26	0.05
	11.78	12.3	0.52	1.02	0.019
	12.3	13.12	0.82	1.49	0.026
	13.3	13.8	0.5	0.498	0.012
	13.8	14.2	0.4	1.06	0.015
	14.2	15	0.8	0.392	0.01
	15	16	1	0.256	0.01

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0068	4.38	5.1	0.72	0.017	0.001
	5.1	6	0.9	0.008	0.002
	6	6.7	0.7	<0.005	<0.001
	6.7	7.57	0.87	<0.005	0.002
	7.57	8.2	0.63	<0.005	<0.001
	8.2	9.03	0.83	<0.005	<0.001
	9.03	9.8	0.77	0.275	0.013
	9.8	10.52	0.72	0.61	0.048
	10.52	10.92	0.4	0.537	0.056
	10.92	11.46	0.54	0.697	0.075
	11.5	12.2	0.7	1.22	0.077
	12.2	13.3	1.1	0.292	0.016
	13.3	14.4	1.1	0.653	0.099
	14.4	15	0.6	0.569	0.1
	15	16	1	1.01	0.069
	16	16.9	0.9	0.927	0.077
	16.9	17.43	0.53	0.395	0.15
	STD	17.43	18.17	0.74	1.05
18.17		19	0.83	0.755	0.115
19		19.88	0.88	1.07	0.106
19.88		20.4	0.52	1.46	0.089
20.4		21.62	1.22	1.99	0.03
21.62		22.1	0.48	0.426	0.015
22.1		23.3	1.2	1.72	0.095
23.3		23.9	0.6	0.934	0.06
24		25	1	0.775	0.078
25		26	1	1.17	0.112
26		26.8	0.8	0.294	0.017
26.8		28.05	1.25	0.246	0.012

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0077A	5.1	6.3	1.2	0.014	<0.001
	6.3	7	0.7	<0.005	<0.001
	7	7.8	0.8	0.067	0.004
	7.8	8.5	0.7	0.33	0.013
	8.5	9.2	0.7	0.445	0.036
	9.2	10	0.8	0.569	0.03
	10	11	1	0.78	0.011
	11	12	1	0.823	0.012
	12	12.4	0.4	0.962	0.021
	12.4	13.1	0.7	0.918	0.071
	13.1	14.1	1	0.908	0.064
	14.1	15.1	1	0.973	0.071
	15.1	15.8	0.7	1.07	0.103
	15.8	16.8	1	1.39	0.11
	16.8	17.8	1	0.849	0.046
	17.8	18.8	1	1.05	0.13
	18.8	19.85	1.05	1.06	0.124
	19.85	20.7	0.85	0.888	0.108
	STD	20.7	21.84	1.14	1.01
22.2		22.97	0.77	0.987	0.124
22.97		23.6	0.63	1.42	0.191
23.6		24.4	0.8	0.897	0.096
24.4		25.54	1.14	0.497	0.061
25.54		26.1	0.56	1.25	0.088
26.1		26.9	0.8	0.331	0.01
26.9		27.6	0.7	1.82	0.022
27.6		28.05	0.45	0.523	0.013
28.1		28.65	0.55	2.12	0.057
28.7		29.4	0.7	2	0.034
29.4		30.4	1	2.15	0.107
30.4		31.15	0.75	1.91	0.062
31.3		32	0.7	1.17	0.05
32		32.76	0.76	1.11	0.028
32.8		33.1	0.3	1.46	0.017
33.1		34	0.9	1.73	0.043
34		35	1	1.8	0.032
35		35.7	0.7	0.55	0.01
35.7		36.5	0.8	0.77	0.026
36.5		37.1	0.6	0.584	0.038
37.1		37.9	0.8	0.295	0.02
37.9		38.8	0.9	1.1	0.058
38.8		39.94	1.14	1.4	0.039
39.94		41.15	1.21	1.14	0.02
41.15		41.5	0.35	0.422	0.011

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0077	0.3	0.95	0.65	0.071	0.002
	0.95	1.7	0.75	0.26	0.012
	1.7	2.3	0.6	0.532	0.028
	2.3	3.3	1	0.805	0.129
	3.3	4.28	0.98	1.03	0.132
	4.28	5.35	1.07	0.42	0.024
	5.35	6.2	0.85	1.28	0.056
	6.2	7	0.8	0.893	0.141
	7	8	1	0.774	0.073
	8	9	1	0.817	0.037
	9	10.07	1.07	1.23	0.221
	10.2	11	0.8	1.57	0.313
	11	11.55	0.55	2.06	0.219
	11.55	12.67	1.12	1.39	0.06
	12.7	13.1	0.4	0.78	0.017
	13.1	13.5	0.4	2.28	0.033
	13.5	14.7	1.2	0.339	0.012

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0080	4.19	4.39	0.2	<0.005	0.002
	4.39	5.41	1.02	0.033	<0.001
	5.41	5.66	0.25	<0.005	<0.001
	5.66	6.9	1.24	0.037	<0.001
	6.9	8.1	1.2	0.031	<0.001
	8.1	9.3	1.2	0.288	0.002
	9.3	10.5	1.2	0.512	0.009
	10.5	11.36	0.86	0.649	0.017
	11.36	11.61	0.25	0.646	0.013
	STD	11.61	12.8	1.19	0.807
12.8		14	1.2	1.1	0.132
14		15.2	1.2	0.974	0.047
15.2		16.13	0.93	1.15	0.111
16.13		16.38	0.25	0.758	0.063
16.38		17.5	1.12	1.27	0.143
17.5		18.7	1.2	1.23	0.137
18.7		19.12	0.42	0.534	0.016
19.2		20.3	1.1	0.627	0.04
20.3		20.97	0.67	1.08	0.054
21		21.54	0.54	1.41	0.054
21.8		22.6	0.8	1.41	0.044
22.6		23.4	0.8	1.46	0.04
23.4		24.3	0.9	0.456	0.013
24.3		24.55	0.25	1.29	0.069
24.55		25.55	1	2.17	0.094
25.55		26.55	1	2.66	0.06
26.55		27.25	0.7	2.28	0.025
27.25		27.5	0.25	1.77	0.019
27.5		28.53	1.03	2.17	0.024
28.53		28.78	0.25	1.95	0.018
28.78		29.6	0.82	2.03	0.025
29.6		30.3	0.7	1.52	0.021
30.3		31	0.7	0.869	0.016
31		31.5	0.5	1.61	0.053
31.5		32.4	0.9	1.42	0.029
32.4		33.35	0.95	1.3	0.025
33.35		34.3	0.95	1.57	0.032
34.3		35.21	0.91	0.335	0.01
35.21		35.45	0.24	0.247	0.01

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0096	0.8	1.65	0.85	0.024	0.002
	1.65	3	1.35	0.024	0.001
	3	3.8	0.8	<0.005	<0.001
	3.85	5.31	1.46	0.013	<0.001
	5.45	6.15	0.7	0.451	0.005
	6.15	7	0.85	0.643	0.011
	7	7.85	0.85	0.735	0.029
	7.85	9	1.15	0.647	0.017
	9	9.85	0.85	0.9	0.029
	9.85	10.65	0.8	0.891	0.017
	10.65	11.35	0.7	0.634	0.023
	11.35	12.7	1.35	0.652	0.023
	12.7	13.65	0.95	0.702	0.043
	13.65	14.85	1.2	0.745	0.095
	14.85	15.65	0.8	0.852	0.122
	15.65	16.45	0.8	0.936	0.063
	16.45	17.27	0.82	0.479	0.035
17.5	18.45	0.95	0.741	0.181	
18.45	19.5	1.05	0.871	0.242	
STD				0.129	0.006

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0096	19.5	20.17	0.67	0.772	0.122
	20.17	21.45	1.28	1.55	0.097
	21.45	22.65	1.2	1.46	0.039
	22.65	24	1.35	0.82	0.044
	24	24.5	0.5	0.932	0.022
	24.5	25.65	1.15	2.45	0.051
	25.65	26.65	1	1.26	0.059
	26.65	27.65	1	1.54	0.095
	27.65	28.17	0.52	0.972	0.041
	28.17	29.25	1.08	2.26	0.08



Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0098A	2.4	3.24	0.84		
	3.24	4.65	1.41		
	4.65	5.35	0.7		
	5.35	6.15	0.8	0.032	<0.001
	6.15	6.95	0.8	0.364	0.046
	6.95	7.65	0.7	0.491	0.063
	7.65	8.65	1	0.416	0.063
	8.65	9.65	1	0.298	0.056
	9.65	10.65	1	0.363	0.093
	10.65	11	0.35	0.311	0.061
	11	12	1	0.686	0.105
	12	13	1	0.766	0.176
	STD	13	13.83	0.83	0.836
13.83		14.6	0.77	0.729	0.093
14.6		15.1	0.5	1.2	0.079
15.1		15.52	0.42	0.412	0.009
15.52		16	0.48	0.66	0.021
16		16.85	0.85	0.655	0.025
16.85		18.03	1.18	0.266	0.01
18.03		19	0.97	0.602	0.015
19		19.9	0.9	0.851	0.024
19.9		21.2	1.3	0.253	0.01

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0098	2.4	3.28	0.88	0.006	0.001
	3.28	4	0.72	0.075	0.006
	4	4.5	0.5	0.33	0.049
	4.5	5.4	0.9	0.278	0.051
	5.4	6.1	0.7	0.248	0.058
	6.1	6.97	0.87	0.355	0.082
	7.1	8.1	1	0.546	0.117
	8.1	8.6	0.5	0.586	0.099
	8.6	9.35	0.75	0.715	0.11
	9.35	10.05	0.7	0.762	0.091
	10.05	10.77	0.72	0.642	0.025
	10.77	11.57	0.8	0.249	0.008

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0100	3.61	3.86	0.25	0.007	0.001
	6.1	6.59	0.49	0.019	<0.001
	6.59	6.84	0.25	0.055	<0.001
	6.84	7.1	0.26	0.214	0.008
	7.1	8.3	1.2	0.685	0.007
	8.3	8.55	0.25	0.813	0.015
	8.55	9.05	0.5	0.569	0.009
	9.05	10.29	1.24	0.767	0.04
	10.29	10.54	0.25	1.34	0.392
	10.54	11.75	1.21	0.803	0.242
	11.75	12.65	0.9	1.02	0.287
	12.65	13.55	0.9	0.829	0.2
	13.55	14.5	0.95	0.827	0.216
	14.6	15.6	1	0.679	0.122
	15.6	16.28	0.68	0.862	0.067
	16.28	16.53	0.25	0.626	0.368
	16.53	17.2	0.67	0.749	0.299
	17.2	18.2	1	0.894	0.101
	18.2	19.23	1.03	0.868	0.166
	19.23	19.53	0.3	1.09	0.028
	19.53	20.4	0.87	0.553	0.089
	20.4	21.4	1	0.431	0.076
	21.4	22.4	1	0.696	0.115
	22.4	23.05	0.65	1.22	0.037
	23.05	23.36	0.31	1.47	0.021
	23.36	23.56	0.2	3.03	0.049
	23.56	24.35	0.79	2.79	0.044
	24.35	24.6	0.25	2.61	0.026
	24.6	25.7	1.1	1.69	0.096
	25.7	26.85	1.15	1.44	0.041
	26.85	27.44	0.59	0.235	0.01
	27.44	27.73	0.29	0.247	0.01

Hole	From (m)	To (m)	Thickness (m)	% Ni	% Co
MAM-KK-0124	5.1	6.3	1.2	0.019	<0.001
	6.3	7.3	1	<0.005	<0.001
	7.3	8.2	0.9	0.024	0.002
	8.2	9.4	1.2	0.214	0.008
	9.4	10.5	1.1	0.318	0.006
	10.5	11.6	1.1	0.46	0.006
	11.6	12.6	1	0.635	0.007
	12.6	13.6	1	0.656	0.046
	13.6	14.65	1.05	0.772	0.07
	14.65	15.7	1.05	0.692	0.087
	15.7	16.4	0.7	0.799	0.106
	16.4	17.1	0.7	0.932	0.372
	17.1	17.8	0.7	0.889	0.208
	17.8	18.75	0.95	0.762	0.097
	18.75	19.7	0.95	0.528	0.06
	19.7	20.3	0.6	0.835	0.098
	20.3	21.55	1.25	1.03	0.429
	21.55	22.8	1.25	1.2	0.592
	22.8	24	1.2	1.33	0.556
	24	24.4	0.4	1.56	0.336
24.4	25.6	1.2	1.28	0.35	
25.6	26	0.4	1.88	0.269	
26	26.2	0.2	LNR	LNR	
STD				LNR	LNR