

Drill Hole	From m	To m	Interval m	La ₂ O ₃ ppm	Ce ₂ O ₃ ppm	Pr ₂ O ₃ ppm	Nd ₂ O ₃ ppm	Sm ₂ O ₃ ppm	Eu ₂ O ₃ ppm	Gd ₂ O ₃ ppm	Tb ₂ O ₃ ppm	Dy ₂ O ₃ ppm	Ho ₂ O ₃ ppm	Er ₂ O ₃ ppm	Tm ₂ O ₃ ppm	Yb ₂ O ₃ ppm	Lu ₂ O ₃ ppm	Y ₂ O ₃ ppm	TREO %
PX039	122.9	142.0	19.2	4,394	7,467	756	2,432	323	82	188	22	96	15	35	5	29	5	440	1.6%
PX040	28.0	43.0	15.0	5,020	7,061	645	2,006	303	90	239	33	164	28	67	9	47	6	844	1.7%
PX045a	9.8	30.9	21.1	2,006	4,148	495	1,833	309	89	217	27	127	20	47	6	33	5	547	1.0%
PX050	8.0	161.0	153.0	2,790	5,578	643	2,353	344	87	214	26	128	21	51	7	40	5	607	1.3%
including	96.0	126.0	30.0	4,370	8,097	890	3,132	430	108	267	32	149	24	57	8	53	7	654	1.8%
including	137.9	161.0	23.2	3,687	7,162	808	2,899	415	105	254	31	145	24	55	7	42	5	651	1.6%
PX053	25.0	61.0	36.0	3,461	6,442	683	2,309	365	98	236	27	117	18	39	4	22	3	492	1.4%
	74.4	94.6	20.2 (i)	2,920	5,507	585	1,972	288	72	169	20	95	15	38	5	24	3	469	1.2%

(i) Includes 2.1m cavity not sampled.