



Massive Sulphide	Flotation							Leached tailings	
	Zn to Zn conc	Pb to Pb conc	Sn to Sn conc	Cu in Pb conc.	Ag in Pb conc.	Au in Pb conc.	Ag in Zn conc.	Ag	Au
Processing recovery	80%	65%	30%	25%	35%	10%	20%	20%	65%
Concentrate grade	48%	45%	10%	2.5%					
Gossan	Flotation		Leaching						
	Pb	Sn	Ag	Au					
Processing recovery	65%	40%	66%	86%					
Concentrate grade	60%	10%							

