

Hole ID	DepthFrom	DepthTo	Interval (m)	Cu_%	Au_g/t	CuEq_%	m% CuEq
CSD-13-001	16	318	302	0.39	0.48	0.82	247.64
	222	322	100	0.65	1.00	1.54	154
CSD-13-002	126	418	292	0.37	0.30	0.64	186.88
	184	226	42	0.50	0.68	1.11	46.62
CSD-13-003	4	751.3	747.3	0.11	0.05	0.15	112.095
	584	712	128	0.23	0.14	0.35	44.8
CSD-13-004	160	318.3	158.3	0.11	0.05	0.15	23.745
CSD-13-005	24	1330	1306	0.62	0.54	1.10	1436.6
	778	1310	532	1.05	1.08	2.01	1069.32
	1052	1310	258	1.27	1.40	2.52	650.16
CSD-14-006	702	1038	336	0.18	0.12	0.29	97.44
CSD-14-007	654	1612	958	0.40	0.17	0.55	526.9
	1056	1294	238	0.65	0.35	0.96	228.48
CSD-14-008	396	1310.5	914.45	0.41	0.44	0.80	731.56
	862	1310.5	448.45	0.56	0.64	1.13	506.7485
	1264	1310.5	46.45	0.71	0.58	1.23	57.1335
CSD-14-009	430	1757.4	1327.35	0.57	0.74	1.23	1632.641
	650	1738	1088	0.66	0.89	1.45	1577.6
	1184	1482	298	1.24	1.72	2.77	825.46
CSD-15-010	446	840	394	0.38	0.36	0.70	275.8
	684	840	156	0.63	0.74	1.29	201.24
CSD-15-011	996	1632	636	0.58	0.40	0.94	597.84
	1412	1518	106	0.73	0.50	1.18	125.08
CSD-15-012	128	1440	1312	0.67	0.63	1.23	1613.76
	438	1440	1002	0.76	0.77	1.45	1452.9
	844	1420	576	1.03	1.19	2.09	1203.84
CSD-15-013	926	1302	376	0.52	0.25	0.74	278.24
	920	1126	206	0.61	0.30	0.88	181.28
CSD-15-014	628	1396	768	0.50	0.45	0.90	691.2
	808	1284	476	0.63	0.65	1.21	575.96
CSD-15-015	na	na	na	na	na	na	na
CSD-16-015R	na	na	na	na	na	na	na
CSD-16-015R2	394	1732	1338	0.49	0.36	0.81	1083.78
	666	1694	1028	0.57	0.42	0.94	966.32
	890	1640	750	0.67	0.50	1.12	840
CSD-16-016	516	1661.6	1145.6	0.63	0.78	1.32	1512.192
	548	1404	856	0.80	1.04	1.73	1480.88
	928	1301.6	373.6	1.00	1.34	2.19	818.184
CSD-16-017	330	1278	948	0.60	0.53	1.07	1014.36
	702	1264	562	0.79	0.75	1.46	820.52
	784	1032	248	1.16	1.36	2.37	587.76
CSD-16-018	466	1670	1204	0.46	0.47	0.88	1059.52
	904	1568	664	0.70	0.77	1.39	922.96
	1174	1436	262	0.91	1.15	1.94	508.28

Data Aggregation Method: Intercepts reported using copper equivalent cutoff grades of 0.1,0.2,0.3,0.5,0.7,1.0 and 1.5% with up to 10m internal dilution, excluding bridging to a single sample. Minimum intersection length 6m. Gold Conversion Factor of 0.89 calculated from a copper price of US\$2.20/lb and a gold price US\$1350/oz.