

Drill Hole	From m	To m	Interval m	La ₂ O ₃ ppm	Ce ₂ O ₃ ppm	Pr ₂ O ₃ ppm	Nd ₂ O ₃ ppm	Sm ₂ O ₃ ppm	Eu ₂ O ₃ ppm	Gd ₂ O ₃ ppm	Tb ₂ O ₃ ppm	Dy ₂ O ₃ ppm	Ho ₂ O ₃ ppm	Er ₂ O ₃ ppm	Tm ₂ O ₃ ppm	Yb ₂ O ₃ ppm	Lu ₂ O ₃ ppm	Y ₂ O ₃ ppm	TREO %	
PX054	23.4	182.0	158.7	2,733	5,233	582	2,097	322	86	205	24	113	18	44	6	34	5	521	1.2%	
PX070	5.0	51.6	46.6	5,228	8,218	785	2,502	318	83	192	21	93	14	30	3	19	3	364	1.8%	
	78.4	201.3	123.0	5,186	8,463	824	2,587	305	77	173	19	82	12	27	3	18	2	330	1.8%	
including	78.4	122.0	43.7	8,194	12,954	1,212	3,596	350	81	173	17	75	11	25	3	18	2	303	2.7%	
PX078	6.0	28.3	22.3	3,214	5,866	621	2,144	332	86	207	24	117	19	44	5	29	4	517	1.3%	
	76.2	144.4	68.3	5,114	8,386	832	2,745	366	90	205	22	103	17	39	5	27	3	482	1.8%	
including	125.1	144.4	19.4	9,581	14,066	1,306	4,063	500	119	250	24	98	14	32	4	20	3	403	3.0%	
PX080	5.7	109.8	104.1	(i) 3,118	5,426	578	2,018	316	82	189	21	94	15	34	4	25	3	406	1.2%	
				(i) Includes 2.1m of core loss not sampled.																
PX081	3.7	57.0	53.3	(i) 6,530	10,274	979	3,058	377	97	243	29	137	22	52	6	36	4	638	2.2%	
including	3.7	30.5	26.8	9,531	14,108	1,290	3,863	440	108	269	32	144	24	56	7	39	5	684	3.1%	
				(i) Includes 3.8m cavity not sampled.																
PX083	31.0	73.2	42.2	2,338	4,551	521	1,961	330	92	228	28	134	21	49	6	31	4	619	1.1%	
PX086	21.5	94.8	73.3	4,503	8,452	903	3,098	431	115	272	32	158	26	61	7	43	5	731	1.9%	
PX087	16.2	90.6	74.4	(i) 5,731	9,603	981	3,234	410	107	247	30	143	23	53	6	36	4	630	2.1%	
				(i) Includes 2.7m cavity not sampled.																