

Locked Cycle Flotation Test Results								
Test	Product	Mass (%)	Assay			Recovery (%)		
			Pb (%)	Zn (%)	Ag (ppm)	Pb	Zn	Ag
LCT1	Pb Conc	2.5	57.47	10.06	1,457	84.30	9.65	90.35
	Zn Conc	3.4	1.16	55.78	38.6	2.25	70.71	3.17
	Zn Cl 1 Scav Tailings	5.3	1.74	2.89	28.8	5.36	5.82	3.76
	Zn Ro Tailings	88.8	0.16	0.41	1.3	8.09	13.82	2.73
	Feed	100.0	1.73	2.65	40.9	100.00	100.00	100.00
LCT2	Pb Cl 3 Conc	2.9	60.01	8.84	1,350	83.72	8.21	87.06
	Zn Cl 3 Conc	4.0	3.07	59.12	66.4	6.01	76.97	6.00
	Zn Cl 1 Scav Tailings	5.5	1.18	1.34	30.9	3.17	2.39	3.83
	Zn Ro Tailings	87.6	0.17	0.44	1.6	7.10	12.44	3.11
	Feed	100.0	2.05	3.09	44.4	100.00	100.00	100.00